

TECHNICAL SHEET PORC RF CMTO CONCRETO BCO 60X60 EXT 1.44

EVALUATED FEATURE		TEST METHOD	NORM ANSI A137.1 REQUIREMENTS (Table 10)	RESULTS		conclusio		
DIMENSIONS								
				(%)	(mm)			
* Nominal Size, mm								
Nominal Size:	600.0 mm							
Manufacturing Size:	600.0 mm	ASTM C499	- 3.00% / 2.00%	0.00	0.00	Comply		
* Caliber Range								
Manufacturing Size:	600.0 mm	A O.T.M. O.400						
Average Size:	600.1 mm	ASTM C499	± 0.25%; ± 0.80mm	0.02	0.10	Comply		
* Warpage Edge,%		ASTM C485	± 0.40%; ± 1.30mm	0.14 0.00	0.82 0.00	Comply		
* Warpage Diagonal, %		ASTM C485	± 0.40%; ± 1.80mm	0.15 0.00	1.28 0.00	Comply		
* Wedging, %		ASTM C502	± 0.25%; ± 0.80mm	0.04 -0.01	0.34 -0.10	Comply		
* Thickness, mm								
Manufacturing:	9.5 mm							
Average result:	9.6 mm	ASTM C499	Max. 1.02 mm	1.05	0.10	Comply		
		PHYSI	CAL PROPERTIES					
* Visible Abrasion Resistance		ASTM C1027	As reported	PE	l IV	-		
* Water Absorption, %		ASTM C373	Impervious Porcelain (P1) wa ≤ 0.5%	0.:	30	Comply		
* Crazing Resistance		ASTM C424	Pass	Appr	roved	Comply		
* Breaking Strength, lbf		ASTM C648	Average ≥ 275	47	70	Comply		
			Individual ≥ 250	45	52	Comply		
* Dynamic coefficient of friction - D	COF	ANSI A137.1						
Wet		Section 9.6	≥ 0.42	0.	49	Comply		
		СНЕМІ	CAL PROPERTIES					
* Chemical Resistance		ASTM C650	As reported	Resi	stant	Comply		
* Stain Resistance		ASTM C1378	As reported	Resi	stant	Comply		
	AL STANDARD SPI	ECIFICATIONS F	ARD, ANSI A137.1. OR CERAMIC TILE / Table 10: Porc		00			

The weight, the tone and the dimensions are subject to some of the typical unavoidable variations of the processes of ceramic cooking.

DATE OF ISSUE	Wednesday, July 21, 2021		
Prepared by: Quality Supervisor	Reviewed by: Manager Quality Assurance		
César Prado R.	Marlene Chauca R.		